

DC Shopprimer HYDRO OptiBase

Water borne shopprimer on an acrylat dispersion basis. Free of lead, cadmium and chromium VI compounds.
Welding certificate of SLV Duisburg (Report no. 2002.P0113.01A)

Field of application

- Temporary protection against corrosion for steel constructions.
- Before using homogenize with mechanical mixer.

Product properties

- Water based
- Fast drying
- Fast recoatability
- Weldable up to 25-30 µm dry film thickness
- Recoatability: universal

Technical Specification

Colours	redbrown , grey. Other colours upon request.
Flash point	Not applicable
Temperature stability	Up to 120 °C
Gloss	Mat
Potential dry film thickness in one working process	25 up to 40 µm
Viscosity	Appr. 30 sec running time (DIN 4 mm pot)
Density in kg/l	1,335
Solid content in %	54
Solid volume in %	37
Theoretical spreading capacity	<ul style="list-style-type: none"> • 14,8 m²/l at 25 µm DFT • 11,09 m²/kg at 25 µm DFT
Recommended film thickness	75 µm WFT corresponds to 30 µm DFT
Drying (DIN EN ISO 1517)	25 µm DFT
Dust-dry (Tg1)	After 10 min
Touch-dry (Tg4)	After 15 min
Dry (Tg6)	After 25 min
Interval for overcoating	<ul style="list-style-type: none"> • after 1 h with water based topcoats • after 24 h with single-component topcoats • after 48 h with two component topcoats
Note	<ul style="list-style-type: none"> • The specifications are based on standard atmospheric conditions 23/50, DIN 50014. • Lower temperatures and/or higher humidity will prolong drying and hardening.

Safety information (See Security Data Sheet)

Solvent content	Appr. 2 % by weight
Aromatic content	Appr. 1 % by weight

Storage

Storage	<ul style="list-style-type: none"> • In dry, cool rooms, frost-proof • Ensure good ventilation
Shelf life	<ul style="list-style-type: none"> • 6 month from date of delivery when in unopened original containers in cool and dry conditions

Application methods

DC Shopprimer HYDRO OptiBase

Airless spraying	<ul style="list-style-type: none"> • Risk of spray dust due to very fast drying • After using the material close the packings immediately • Dip the pistol and the nozzle into water during the breaks • It is tending to fast skinning. Do not stir the skin in any case! • Flow pressure 70 - 100 bar • Nozzle size 0,007 - 0,017 inch (0,18 - 0,43 mm) • Suitable for the application on automatical equipments
Compressed air spraying	<ul style="list-style-type: none"> • Can be applied as delivered • Spraying pressure 4 bar • Nozzle size 1,3 - 1,5 mm
Electrostatic application	<ul style="list-style-type: none"> • Application is possible, provided the equipment is suitable for water based materials
Dipping	<ul style="list-style-type: none"> • Can be applied as delivered
Other methods	<ul style="list-style-type: none"> • Roller and brush application for repair work is possible
Thinner	<ul style="list-style-type: none"> • Max. 3% Water
Cleaning	<ul style="list-style-type: none"> • Rinse immediately with Wasser • Residues are dissolvable with Deripox-Verdünnung
Preparation of support	<ul style="list-style-type: none"> • Shot blasting to a purity according to SA 2½ • Mill scale, welding residues, dust and dirt on the surface which might reduce adhesion have to be carefully and thoroughly removed
General remarks	<ul style="list-style-type: none"> • During coating and drying the humidity should be min. 30 % / max. 85 % • Object temperature at least 3° C above dew point.
Example for a system	<ul style="list-style-type: none"> • Primer coat: DC Shopprimer HYDRO OptiBase • Finish coat: Miscellaneous

The general information and descriptions contained in this specification are provided to the best of our knowledge. Our information and specifications do not constitute warranted characteristics in the legal sense. Any advice for preparation and application which may be provided verbally, in writing or by means of experiments is of general nature only, and any property rights of third parties are also to be regarded in this context. Our general instructions do not release you from your obligation to check the suitability of the products supplied by our company for the intended methods and purposes of application. Particular in those cases when our supplied material will be applied with products from other sources. The products are prepared, applied and used outside of our sphere of control and thus fall solely within the user's scope of responsibility.

Our general terms of sale and delivery apply as agreed.

Product group: AG7076351000